

Ites Gummi- und Dichtungstechnik GmbH Stedinger Str. 29, D-26723 Emden Deutschland Telefon: +49 (0)4921/99370-0, Fax: +49 (0)4921/99370-27 e-mail: info@ites-gummi.de, internet: www.ites-gummi.de

## Technical Data Sheet Cellular Rubber EPDM

Celluar Rubber EPDM, closed cell structure, low absorbtion of water, high resistance to ozone.

Technical Data*:	
Colour	black
Density:	0,15
Shore Hardness:	35 +/-6 Shore 00
Tensile strength:	> 350 kPa nach ISO 1798
Elongation:	150%
Temperature range:	-40° - +100° C
*approximately	

Chemical Resistance:	<b>Recommendation:</b>	Available Dimmensions:		
Oil resistance:	-	Thickness	Width/Length:	Format:
Bezine resistance:	-	02-20 mm	1 x 10 m	roll
Acid resistance:	+	20-50 mm	1 x 2 m	sheet
Strong bases:	+			
Ozone - and weather resistance:	++			
Abrasion:	-			

## **General Information:**

## Legend for recommendation of chemical resistance:

## ++ = excellent; + = acceptable; 0 = moderately; - = non resistant

\*\* The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage.